CME 40

GET-WELL!

MADE BY DUVATEX

Technical specifications

Piece density:	***ISO 845***		39 kg/m³
Compression hardness	***ISO 3386 (CLD/40 %)***		3,9 kPa
Indentation hardness	***ISO 2439/B (ILD)***	25%	125 N
		40%	160 N
		65%	320 N
Compression set:	***ISO 1856/A(75%)***		<7 %
Elongation at break:	***ISO 1798***		>120 %
Tensile strength:	***ISO 1798***		>80 kPa
Tear strength:	***ISO 8067***		>250 N/m
Resilience:	***ASTM D 3574/H***		>40 %
Fire tests:	***MVSS 302***		<100 mm/min
	M4		pass
	BS5852/source 5 (*)		pass
	BS7177		pass
Fire safety	***CRIB5***		
Anti bacterial:	***Bacteriumstatic treated against pathogenic and allergen micro organisms***		

(*) The Furniture and Furnishings (Fire) (Safety) Regulations 1988 Schedule 1 / Part 1