GET-WELL!

MADE BY DUVATEX

# CMHR 55

**Description**

* cold foam HR has an open cell structure, is anti-mould and durable
* very good elasticity and moisture regulation
* elastic, long lasting and high-quality sleep comfort

**Technical specifications**

| | | | |
|---|---|---|---|
| ***Piece density:*** | ***ISO 845*** | | 50 kg/m³ |
| ***Compression hardness*** | ***ISO 3386 (CLD/40 %)*** | | 3,6 kPa |
| ***Indentation hardness*** | ***ISO 2439/B (ILD)*** | 25% | 110 N |
| | | 40% | 145 N |
| | | 65% | 290 N |
| ***Compression set:*** | ***ISO 1856/A(75%)*** | | <5 % |
| ***Elongation at break:*** | ***ISO 1798*** | | >140 % |
| ***Tensile strength:*** | ***ISO 1798*** | | >90 kPa |
| ***Tear strength:*** | ***ISO 8067*** | | >250 N/m |
| ***Resilience:*** | ***ASTM D 3574/H*** | | >60 % |
| ***Fire tests:*** | ***MVSS 302*** | | <100 mm/min |
| | ***M4*** | | pass |
| | ***BS5852/source 5 (*)*** | | pass |
| ***Fire safety*** | ***CRIB5*** | | |
| ***Anti bacterial:*** | ***Bacteriumstatic treated against pathogenic and allergen micro organisms*** | | |

(*) The Furniture and Furnishings (Fire) (Safety) Regulations 1988 Schedule 1 / Part 1