COVER M

GET-WELL!

MADE BY DUVATEX

M COVER LIGHT

Description

Basic bi-elastic polyurethane on polyester basis

Technical specifications

Composition:		Coating	105	g/m²
		Fabric	100	g/m²
		Total	205	g/m²
Tensile strength:	***ISO 1421***	Warp	> 35	daN/5cm
		Weft	> 18	daN/5cm
Elongation:		Warp	> 120	%
		Weft	> 250	%
Tear strength:	***ISO 4674***	Warp	> 2.0	daN/5cm
		Weft	> 2.0	daN/5cm
% Elongation at 30N Tensile strength:		Warp	> 120	%
		Weft	> 90	%

Hydrostatic head:	***ISO 1420***	> 200 %
Hydrolisis:	***Jungle test***	after 3 weeks: no loss of quality
Flex resistance:	***ISO 5402***	at 200000: no loss of quality
Watervaporpermeability:	***ASTM96-66***	<1950 g/m² - 24 h at 38° C
Biocomptability:	***10.993-10***	Rapport: LEMI/MATILLAC - non allergic

Is treated: ***FIRE RESISTANT: BS 7175 CRIB 7*** (Centexbel rapport 12.04776.01)
ANTI BACTERIE & MRSA PROOF: Sanitized Clariant Benelux
ANTI HOUSE DUST MITE

Resistance to desinfectans:	Denaturated alcohol:	90 % alcohol + 2 % ether
	Fugaten spray	ethanol 70 % (608 g/l)
	Other	oils (g/l) 5 min. contact
		H.A.C., Reocid, Dettol, Lyorthol,
		Indur Des, Respect, Hycolin, Clearsol
Cleaning:	***ISO 6330***	No loss of quality after 30 washings

