P COVER POLYAMIDE

GET-WELL!

MADE BY DUVATEX

Backing: 100 % Polyamide; Coating: 100% Polyurethane

Technical specifications

Composition:		Coating	125	g/m²
		Fabric	130	g/m²
		Total	255	g/m²
Tensile strength:	***ISO 1421***	Length	> 50	daN/5cm
	1998	Width	> 30	daN/5cm
Elongation under 30N/5cm:		Length	> 25	%
		Width	> 40	%
Tear strength:	***ISO 4674-01***	Length	> 3.0	daN
	2003	Width	> 3.0	daN
Seam resistance:	***ISO 13936-1***	Length	> 24	daN/5cm
	2004	Width	> 24	daN/5cm
Coating to fabric adhesion:	***ISO 2411***		> 3.0	daN/5cm
	2000			

Hydrostatic head:	***ISO 1420***	> 200 %
Hydrolisis:	***Jungle test***	after 3 weeks: no loss of quality
Flex resistance:	***ISO 5402***	at 200000: no loss of quality
Watervaporpermeability:	***ASTM E96***	>750 g/m² - 24 h (Centexbel rapport 14.01383.03 2014)
Biocomptability:	***10.993-10***	Bioserv 2014010110 2014

Is treated:

FIRE RESISTANT: BS 7175 CRIB 5 (Centexbel rapport 49044 09/01/06)
ANTI BACTERIE: Sanitized Clariant Benelux (licence nr. 1231.99)
ANTI HOUSE DUST MITE

Oekotex 100 Class 1

Resistance to desinfectans: Recommendation of water and soap only
A list of approved desinfectants can be sent

Cleaning:

